



131 East Main Street, West Brookfield, MA 01585
(508) 867-5244 · www.gremarco.com · info@gremarco.com

SERIES AA27

TECHNICAL DATA SHEET

Activated Alumina Impregnated Filter Media

1. Product Description

This media is engineered for desiccant-grade moisture and fluoride removal for demanding industrial filtration. The activated alumina is bonded directly to a non-woven polyester substrate (10.0 oz./sq.yd. uncoated), producing a flexible media that is easy to handle and integrate into OEM converting and manufacturing processes.

2. Base Fabric / Substrate

Uncoated Weight: 10.0 oz./sq.yd.

Composition: Non-woven Polyester

3. Technical Specifications

Style No.	AA2750	AA2760	AA2767
Activated Alumina Add-On (%)	100	150	200
Activated Alumina (grams/sq.yd.)	283.5	425.3	567.0
Total Coated Weight (oz./sq.yd.)	20.0	25.0	30.0
Nominal Thickness (inches)	0.625"	0.625"	0.625"

Other activated alumina loadings, thicknesses, and air flow options available — contact Gremarco to discuss your requirements.

4. Certifications & Regulatory Compliance

- Conflict Minerals, TSCA, California Prop 65, REACH, RoHS, and PFAS declarations available at gremarco.com/disclosures
- Safety Data Sheet (AA Series SDS) available at gremarco.com/disclosures

5. Packaging

Standard put-up is 48" wide rolls, approx. 30 linear yards per roll. Rolls can be slit to width or die cut to your exact specifications upon request.

6. Handling & Storage

- Store sealed in a cool, dry environment
- Avoid rough handling to prevent dusting
- Keep away from strong oxidizers (e.g., liquid oxygen)

The information provided is believed to be accurate and representative of the product(s) listed. Gremarco, LLC makes no warranty, either expressed or implied, regarding the suitability of any product(s) listed for any specific use. This Technical Data Sheet does not replace the Safety Data Sheet (SDS); refer to the AA Series SDS at gremarco.com/disclosures for complete handling and safety information.